

No	DIN NORMU	C(Max)	Si	Mn	P	S	Pb ²
1.0711	9 S 20	0.13	0.05	0.60-1.20	0.100	0.180-0.250	-
1.0715	9 SMn 28	0.14	0.05	0.90-1.30	0.100	0.240-0.320	-
1.0718	9 SMnPb 28	0.14	0.05	0.90-1.30	0.100	0.240-0.320	0.15-0.30
1.0736	9 SMN 36	0.15	0.05	1.00-1.50	0.100	0.320-0.400	
1.0737	9 SMnPb 36	0.15	0.05	1.00-1.50	0.100	0.320-0.400	0.15-0.30
1.0721	10 S 20	0.07-0.13	0.10-0.40	0.50-0.90	0.060	0.150-0.250	-
1.0722	10SPb20	0.07-0.13	0.10-0.40	0.50-0.90	0.060	0.150-0.250	0.15-0.30
1.0726	35 S 20	0.32-0.39	0.10-0.40	0.50-0.90	0.060	0.150-0.250	-
1.0727	40 S 20	0.42-0.50	0.10-0.40	0.50-0.90	0.060	0.150-0.250	-