

| No | DIN NORM | C(Max) | Si | Mn | P | S | Pb² |
|---------------|---------------------|---------------|-----------|-----------|----------|-------------|-----------------------|
| 1.0711 | 9 S 20 | 0.13 | 0.05 | 0.60-1.20 | 0.100 | 0.180-0.250 | - |
| 1.0715 | 9 SMn 28 | 0.14 | 0.05 | 0.90-1.30 | 0.100 | 0.240-0.320 | - |
| 1.0718 | 9 SMnPb 28 | 0.14 | 0.05 | 0.90-1.30 | 0.100 | 0.240-0.320 | 0.15-0.30 |
| 1.0736 | 9 SMN 36 | 0.15 | 0.05 | 1.00-1.50 | 0.100 | 0.320-0.400 | |
| 1.0737 | 9 SMnPb 36 | 0.15 | 0.05 | 1.00-1.50 | 0.100 | 0.320-0.400 | 0.15-0.30 |
| 1.0721 | 10 S 20 | 0.07-0.13 | 0.10-0.40 | 0.50-0.90 | 0.060 | 0.150-0.250 | - |
| 1.0722 | 10SPb20 | 0.07-0.13 | 0.10-0.40 | 0.50-0.90 | 0.060 | 0.150-0.250 | 0.15-0.30 |
| 1.0726 | 35 S 20 | 0.32-0.39 | 0.10-0.40 | 0.50-0.90 | 0.060 | 0.150-0.250 | - |
| 1.0727 | 40 S 20 | 0.42-0.50 | 0.10-0.40 | 0.50-0.90 | 0.060 | 0.150-0.250 | - |